

TEST REPORT

Report No. : MAN:HL:1448000403

ISSUE DATE: 06th February, 2023



MAX SPARE LTD.
 KHOPOLI-RAIGAD, MAHARASHTRA-410203
 INDIA
CONTACT PERSON : MUBIN SHAIKH

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION SILICONE FOOD GRADE RUBBER (VMQ) SL-FG
COLOUR GREEN
STYLE NO. SL70 FG
CONDITION OF SAMPLE COMPLETE AND OK

THE LOCATION OF PERFORMANCE OF THE LABORATORY ACTIVITIES: SGS GURUGRAM LABORATORY

LAB PROVIDED DETAILS :


SAMPLE RECD ON 18/01/2023
TEST PERFORMING DATE 20/01/2023 TO 06/02/2023

SUMMARY OF TEST RESULTS:

TEST REQUESTED	CONCLUSION
European Commission Directive 93/11/EEC and Council of Europe Resolution AP (2004) 4	--
Overall Migration	Pass

TEST(S) RESULT & METHOD: PLEASE REFER TO NEXT PAGE(S). RESULTS APPLY TO THE SAMPLE AS RECEIVED

Per Pro SGS India Pvt. Ltd.



SANDIP BHUSHAN (Technical Manager)
Authorized Signatory

Email your Test Report Related Enquiries at Feedback.HLT@sgs.com

TEST REPORT

Report No. : MAN:HL:1448000403

ISSUE DATE: 06th February, 2023



TEST RESULTS:-

European Commission Directive 93/11/EEC and Council of Europe Resolution AP (2004) 4:

OVERALL MIGRATION:-

Method: With reference to Commission Regulation (EU) No 10/2011 of 14th January 2011 Annex III and Annex V for selection of condition and EN 1186-1:2002 for selection of test methods. (1st Migration);
EN 1186-3:2002 by Total Immersion method.


Simulant Used	Test Condition	Result (mg/dm ²)	Reporting Limit (mg/dm ²)	Permissible Limit (mg/dm ²)
10% Ethanol	40°C for 10 Days	Not Detected	2.0	10
Conclusion	--	Pass	--	--

Tested Item: SILICONE FOOD GRADE RUBBER (VMQ) SL-FG

Note :-

1. mg/dm² = milligram per square decimeter
2. °C = degree Celsius
3. Permissible Limit is according to Commission Regulation (EU) No 10/2011 of 14th January 2011 with amendments.
4. Analytical tolerance of aqueous simulants is 2mg/dm² or 12mg/kg
5. Test condition & simulant were specified by customer.
6. Testing has been subcontracted to SGS Gurugram lab.

Samples as Received



***** END OF REPORT*****