

Material: Acrylonitrile Butadiene Rubber (NBR) MAX SPARE Code: NT 70

| Physical properties | Nominal | Units |
|-------------------------------|-------------|--------------------|
| Hardness | 70-75 | Shore A |
| ASTM D 2240, 23°C | | |
| Tensile strength | > 102 | Kg/cm ² |
| ASTM D 412, 23°C | | |
| Elongation at break | > 250 | % |
| ASTM D 412, 23°C | | |
| Compression set | < 25 | % |
| ASTM D 395, 100°C, 22 h, 25 % | | |
| Air Ageing | | |
| ASTM D 573, 100°C, 70 h | | |
| Hardness Change | <(+15) | Points |
| Tensile Change | <(-20) | % |
| Elongation Change | <(-40) | % |
| Fluid Resistance, IRM-901 | | |
| ASTM D 471, 100°C, 70 h | | |
| Hardness Change | -5 to+15 | Points |
| Tensile Change | <(-25) | % |
| Elongation Change | <(-45) | % |
| Volume Change | -10 to +5 | % |
| Fluid Resistance, IRM-903 | | |
| ASTM D 471, 100°C, 70 h | | |
| Hardness Change | <(-15) | Points |
| Tensile Change | <(-45) | % |
| Elongation Change | <(-45) | % |
| Volume Change | 0 to +35 | % |
| Specific Gravity | 1.22 ± 0.02 | g/cc |
| ASTM D 792, 23°C | | |
| Ash Content | <(5) | % |
| 800°C, 2 Hrs | | |
| Service Temperature | -30 to 100 | °C |

Disclaimer